



# T114A



## SATO Ribbons | Fast Wax

- Resin Enhanced
- Excellent Image Density
- Maximizes Barcode Scanning Rates
- Print Speeds up to 12 ips
- Prints on Coated Labels & Tags
- Best Performance for High-Speed Solution
- High Smudge & Scratch Resistance
- Prints at Low Print Head Energy Heat Settings



## Fast Wax Thermal Transfer Ribbon

RIBBON PROPERTY	
Base Material	Polyester Film
Ink Color	Black
Transmission Density	1.95
Back Coating	Yes
Total Thickness	7.1 ± 0.3 µm
Ink Thickness	2.8 ± 0.2 µm
Electrostatic	≤ 0.06 Kv
Optical Density	≥ 1.82 D
Ink Melt Point	154.4°F / 68°C
PRINTING PROPERTY	
Image Density	High
Recommended Substrates	Art paper, coated and uncoated paper, tag stocks, and vellums
DURABILITY OF PRINTED IMAGE	
Smudge Resistance	High
Scratch Resistance	Good
Storage Condition	40°-90°F (5-35°C), 20-85% RH
Storage Life	1 Year after manufacturing

The above data represents product averages, allowing for industry accepted variances. These products should be tested in the end-use conditions to ensure that they meet the requirements of the specific application. Specification may change without notice.

### SATO AMERICA CORPORATE

10350-A Nations Ford Rd  
Charlotte, NC 28273  
Phone: (704) 644-1650  
Fax: (704) 644-1662  
sales-sallc@sato-global.com

### LABEL MANUFACTURING, SERVICE & SALES

UNITED STATES MEXICO CENTRAL AMERICA  
CANADA CARIBBEAN

[www.satoamerica.com](http://www.satoamerica.com)

©2018 SATO America. All rights Reserved. Rev A • Any unauthorized reproduction of this content, in part or whole, is strictly prohibited • SATO is a registered trademark of SATO Corporation and its subsidiaries in Japan, the U.S. and other countries. All other trademarks are the property of their respective owners.